

Lámina rolada en frio

CAL	JBRES Y	/ ESPESOF	RES STD.	1000	8 8		PESO POR	HOJA EN K	ILOGRAM	OS
Calibre	mm	Pig	Rango Pig	Kg/m2	Lb/Pie2	3' x 6'	3' x 8'	3' x 10'	4' x 8'	4' x 10'
4	5.69	0.22	0.02 0.22	44.67	9.15	74.79	99.72	124.65	132.96	166.20
5	5.31	0.21	0.22 0.20	41.68	8.54	69.80	93.06	116.33	124.08	155.10
6	4.94	0.19	0.20 0.19	38.78	7.94	64.93	86.58	108.22	115.44	144.30
7	4.55	0.18	0.19 0.17	35.72	7.32	59.81	79.74	99.68	106.32	132.90
8	4.18	0.16	0.17 0.16	32.81	6.72	54.94	73.26	91.57	97.68	122.10
9	3.80	0.15	0.16 0.14	29.83	6.11	49.95	66.60	83.25	88.80	111.00
10	3.42	0.13	0.14 0.13	26.85	5.50	44.95	59.94	74.92	79.92	99.90
1/8	3.18	0.13	0.13 0.12	24.96	5.11	41.80	55.73	69.67	74.31	92.89
11	3.04	0.12	0.13 0.11	23.86	4.89	39.96	53.28	66.60	71.04	88.80
12	2.66	0.10	0.11 0.10	20.88	4.28	34.96	46.62	58.27	32.16	77.70
13	2.28	0.09	0.10 0.08	17.90	3.67	29.97	39.96	49.95	53.28	66.60
14	1.90	0.07	0.08 0.07	14.92	3.06	24.97	33.30	41.62	44.40	55.50
15	1.71	0.07	0.07 0.06	13.42	2.75	22.48	29.97	37.46	39.96	49.95
16	1.52	0.06	0.06 0.05	11.93	2.44	19.98	26.64	33.30	35.52	44.40
17	1.37	0.05	0.06 0.05	10.76	2.20	18.01	24.01	30.01	32.01	40.20
18	1.21	0.05	0.05 0.04	9.50	1.95	15.90	21.21	26.51	28.28	35.34
19	1.06	0.04	0.05 0.04	8.32	1.70	13.93	18.58	23.22	24.77	30.96
20	0.91	0.04	0.04 0.03	7.14	1.46	11.96	15.95	19.94	21.26	26.58
21	0.84	0.03	0.04 0.03	6.59	1.35	11.04	14.72	18.40	19.63	24.54
22	0.76	0.03	0.03	5.97	1.22	9.99	13.32	16.65	17.76	22.20
23	0.68	0.03	0.03 0.02	5.34	1.09	8.94	11.92	14.90	15.89	19.86
24	0.61	0.02	0.03 0.02	4.79	0.98	8.02	10.69	13.36	14.25	17.82
25	0.53	0.02	0.02 0.02	4.16	0.85	6.97	9.29	11.61	12.38	15.48
26	0.45	0.02	0.02 0.02	3.53	0.72	5.91	7.89	9.86	10.52	13.14
27	0.42	0.02	0.02 0.01	3.30	0.68	5.52	7.36	9.20	- }	
28	0.38	0.01	0.02 0.01	2.98	0.61	4.99	6.66	8.32		
29	0.34	0.01	0.02 0.01	2.67	0.55	4.47	5.96	7.45		
30	0.30	0.01	0.01 0.01	2.36	0.48	3.94	5.26	6.57		
32	0.25	0.01	0.01 0.01	1.93	0.40	3.24	4.32	5.40		
34	0.21	0.01	0.01 0.01	1.64	0.34	2.74	3.65	4.56		